

Certificate of test

Particle size distribution (by washing and sieving)



Prepared in accordance with BS EN 933-1: 2012

Prepared in accordance with BS EN 932-2: 1999

Laboratory Reference: **OCMT-7140-3194**

Client: **Towens of Weston Ltd**

Clients Address: **Plot 2, Warne Road, Weston Super Mare, BS23 3UU**

Site: **Westonzoyland**

Certificate Reference: **OCMT-7140-3194-A03-WS**

Issue Number: **1.1**

Client Order Number: **Towens-Monthly Westonzoyland**

Sample Reference: **20/40mm S/S Reclaimed Coarse Aggregate**

Source: **Ex-site**

Location of Sample on Site: **Production Pile**

Material Description: **20/40mm S/S Reclaimed Coarse Aggregate**

Clients Indicated Specification: **EN 12620: 20/40 Gravel/Recycled (Gc85/20)**

Sample Certificate: **Yes - See enclosed**

Date Sampled: **19/1/2024**


Sampled by: **ST (OEMA)**

Date Received: **19/01/2024**

Date Tested: **31/01/2024**

Result:

| ISO 565 Sieve Aperture (mm) | Percentage Passing (%) | Specification (Passing) | |
|-----------------------------|------------------------|-------------------------|-----------|
| | | Lower (%) | Upper (%) |
| 125.00 | 100 | | |
| 80.00 | 100 | 100 | 100 |
| 63.00 | 100 | 98 | 100 |
| 40.00 | 97 | 85 | 99 |
| 31.50 | 64 | | |
| 20.00 | 3 | 0 | 20 |
| 16.00 | 2 | | |
| 14.00 | 2 | | |
| 10.00 | 1 | 0 | 5 |
| 8.00 | 1 | | |
| 6.30 | 1 | | |
| 4.00 | 1 | | |
| 2.80 | 1 | | |
| 2.00 | 1 | | |
| 1.00 | 1 | | |
| 0.500 | 1 | | |
| 0.250 | 1 | | |
| 0.125 | <1 | | |
| 0.063 | 0.4 | 0 | 1.5 |



Fractions where required (differences in values passing selected sieves)

| | | | |
|--|--|--|--|
| | | | |
| | | | |
| | | | |

Uniformity Co-efficient

| | | | |
|-----------|------|--|--|
| D100 (mm) | 63 | | |
| D60 (mm) | 30.7 | | |
| D10 (mm) | 21.3 | | |
| U/C (nr.) | 1.44 | | |

Remarks: **This sample complies with the clients indicated grading specification**

Approved By: **Martin Slater - Material Technologist**
 Date Approved: **14/02/2024**
 Sheet Ref: **A03-WS-Rev6-Nov23**

Refer to the remarks section for any additions, deviations or exclusions from the stated test & preparation methods. The results within this test report are representative of the samples submitted at the time of analysis. This test report should not be reproduced, except in full, without the express permission of the issuing laboratory. Bulk samples are retained for a period of 28 days from receipt. Any opinions or interpretations indicated are outside the scope of our accreditation. Simplified decision rules apply to any statements of compliance made on the test report. Where a sample has not been taken by Oema Chem Ltd, the test results apply to the sample as received.

Oema Chem Limited
T/A OEMA
 Unit 1 - Building 267A
 Commercial Road
 Christchurch
 Dorset
 BH23 6NW

